

ガラス品種構成			光学的性能							熱的性能						遮蔽係数	日射熱取得率	遮蔽係数	日射熱取得率	遮蔽係数	日射熱取得率
			可視光		日射			紫外線	熱貫流率												
			透過率 (%)	反射率 OUT (%)	透過率 (%)	反射率 OUT (%)	吸収率 (%)		透過率 (%)	W/m ² K			kcal/m ² h [°] C			S・C	η	S・C	η	S・C	η
								乾燥空気		アルゴン	クリプトン	乾燥空気	アルゴン	クリプトン	乾燥空気						
ガラス1	中空層1	ガラス2																			
DLGP3	6	FL3	78.7	13.4	50.5	32.4	17.1	31.1	2.5	2.0	1.4	2.2	1.8	1.2	0.64	0.55	0.64	0.54	0.64	0.54	
DLGP3	12	FL3	78.7	13.4	50.5	32.4	17.1	31.1	1.7	1.3	1.1	1.4	1.1	0.91	0.64	0.54	0.64	0.54	0.63	0.54	
DLGP3	16	FL3	78.7	13.4	50.5	32.4	17.1	31.1	1.4	1.2	1.1	1.2	0.99	0.94	0.64	0.54	0.63	0.54	0.63	0.54	
DLGP3	5	F4	78.3	13.4	49.7	32.4	17.9	30.2	2.8	2.3	1.6	2.4	1.9	1.4	0.64	0.55	0.64	0.54	0.64	0.54	
DLGP3	11	F4	78.3	13.4	49.7	32.4	17.9	30.2	1.8	1.4	1.1	1.5	1.2	0.90	0.64	0.54	0.63	0.54	0.63	0.54	
DLGP3	15	F4	78.3	13.4	49.7	32.4	17.9	30.2	1.4	1.1	1.1	1.2	0.99	0.93	0.64	0.54	0.63	0.54	0.63	0.54	
DLGP3	16	F4	78.3	13.4	49.7	32.4	17.9	30.2	1.4	1.2	1.1	1.2	0.99	0.94	0.64	0.54	0.63	0.54	0.63	0.54	
DLGP3	8	FL3M30FL3	77.7	13.2	46.8	32.2	21.0	0.0	2.1	1.7	1.2	1.8	1.5	1.0	0.63	0.54	0.63	0.54	0.63	0.54	
DLGP3	12	FL3M30FL3	77.7	13.2	46.8	32.2	21.0	0.0	1.6	1.3	1.1	1.4	1.1	0.91	0.63	0.54	0.63	0.54	0.63	0.54	
DLGP3	16	FL3M30FL3	77.7	13.2	46.8	32.2	21.0	0.0	1.4	1.1	1.1	1.2	0.99	0.93	0.63	0.54	0.63	0.54	0.63	0.54	
DLGP4	10	FL4	77.9	13.3	48.8	30.5	20.7	29.4	1.9	1.5	1.0	1.6	1.3	0.89	0.63	0.53	0.63	0.53	0.62	0.53	
DLGP4	14	FL4	77.9	13.3	48.8	30.5	20.7	29.4	1.5	1.2	1.1	1.3	1.0	0.92	0.63	0.53	0.62	0.53	0.62	0.53	
DLGP4	16	FL4	77.9	13.3	48.8	30.5	20.7	29.4	1.4	1.2	1.1	1.2	0.99	0.93	0.63	0.53	0.62	0.53	0.62	0.53	

